

INFLUENCE OF AGGLOMERATION PHENOMENON IN MACHINING OF AISI
D2 HARDENED STEEL USING NANO CHROMIUM POWDER MIXED-EDM

MOHAMMED ABDULRIDHA ABBAS

A thesis submitted in
fulfillment of the requirement for the award of the
Doctor of Philosophy of Mechanical Engineering

Faculty of Mechanical and Manufacturing Engineering
Universiti Tun Hussein Onn Malaysia

May 2020

“I dedicate this effort to the biggest hearts who made me a good man: my dear mother, my late father Abdulridha Abbas, to my partner in dreams and ambitions my loving wife, to my dear son, to all who supported and prayed for me, I would like to tell them, I thank you from my heart and ask Allah to accept this work. Ameen yarab.”



ACKNOWLEDGEMENTS

بِسْمِ اللَّهِ الرَّحْمَنِ الرَّحِيمِ

In the name of Allah the Most Merciful

Alhamdulillah and blessings to the Messenger of Allah, Mohammad, and his family and companions. This thesis would not have been possible without the guidance and the help of several individuals who in one way or another contributed and extended their valuable assistance in the preparation and completion of this study.

First and foremost, this dissertation would not have been possible without the help, support and patience of my supervisor, Prof. Dr. Hj. Mohd Amri Bin Lajis, whom I would like to thank with all my heart for his cooperation with me to complete my research, not to mention his advice and unsurpassed knowledge in the field of Powder Mixed-EDM.

Also, I would like to present a special thanks to Assoc. Prof. Dr. Erween Bin Abd Rahim, and to the teams of PREMACH and SMART for hosting me throughout my research duration and for helping me. I would like to thank Mr. Faizal, Hj. Tarmizi and Mr. Anuar for their role in teaching, supporting, and helping me perform the machining in EDM and observing in SEM/EDS. My special thanks also to the Ceramic Lab team.

I also wish to sincerely thank the Ministry of Higher Education and Scientific Research, Malaysia, represented by Universiti Tun Hussein Onn Malaysia (UTHM), especially the Faculty of Mechanical and Manufacturing Engineering. Additionally, I present a special thanks to the Ministry of Higher Education and Scientific Research, Iraq, for academically supporting all Iraqi students. Last but not least, my special thanks to my mother and my wife, and all who supported me.

ABSTRACT

The Powder Mixed-Electrical Discharge Machining (PMEDM), as an influential environment, has been proven to overcome the challenges of dielectric liquids impedance, machinability, and surface integrity problems. Also, the additive powder particles played a vital role in this enhancement. Nevertheless, this environment suffers from the powder agglomeration phenomenon, as abnormal behaviour, resulting in the dropping of the performance of PMEDM. Accordingly, the present work aims to neutralize this phenomenon during machining AISI D2 hardened steel in PMEDM environment by employing 10, 15, and 20 Amps; 20, 25, and 30 μ s; 2, 4, and 6 g/L for peak current (I_p), pulse duration (T_{on}), Nano Chromium Powder (NCP) concentration (P_C), respectively. These parameters, which are produced by Finite Element Analysis (FEA), predicted the boundaries, as the pilot procedure, to avoid the collapse of the removal operation. Digital Balance, SJ400 Mitutoyo, Shimadzu Vickers's tester, and SEM/EDS-Hitachi SU-1510 were invested to specify the Material Removal Rate (MRR), Tool Wear Rate (TWR), average surface roughness (R_a), Microhardness (MH), Recast Layer Thickness (RLT), and agglomeration ratio (%AG) after machining. Depending on Energy Dispersive X-Ray Spectroscopy (EDS) observations before and after machining stages, the weight percentage of chromium element reduced from 7.78% to (3.12% to 6.68%). Hence, NCP particles have not agglomerated in the interelectrode gap zone. Furthermore, the carbon and other elements agglomeration contributed in enhancing the microhardness from (655 to 675) HV to (784 to 911.65) HV. The Technique for Order of Preference by Similarity to Ideal Solution (TOPSIS)-Analyses of Variance (ANOVA)-Response Surface Methodology (RSM), as hybrid optimization, boosted the composite desirability of Multiple-Response optimization produced by RSM from 0.6153 to 0.9997. Moreover, this hybrid technique has determined $I_p = 10$ Amps, $T_{on} = 30$ μ s, and $P_C = 2$ g/L; $I_p = 20$ Amps, $T_{on} = 20$ μ s, and $P_C = 6$ g/L, as the optimal and worse cases, respectively. Accordingly, the predictive cost, according to the optimal-case, has declined by 40.23% as compared to the worse case.

ABSTRAK

Pemesinan nyahcas elektrik dengan campuran serbuk (PMEDM) telah terbukti sebagai satu kaedah teknologi pemesinan berdaya maju yang dapat mengatasi masalah impedans cecair dielektrik, kebolehmesanan dan masalah kualiti kekasaran permukaan. Partikel-partikel bahan tambah serbuk juga memainkan peranan penting dalam proses penggalakan tersebut. Namun begitu fenomena aglomerasi serbuk semasa PMEDM berlangsung telah mengakibatkan penurunan prestasi pemesinan tersebut. Maka, dalam kajian ini, proses peneutralan aglomerasi serbuk semasa pemesinan keluli tempa keras AISI D2 semasa PMEDM telah dijalankan dengan beberapa parameter seperti Arus puncak (I_p) - 10, 15, dan 20 amps, Tempoh denyutan (T_{on}) - 20, 25, dan 30 μs ; dan Kepekatan serbuk kromium-nano (NCP) - 2, 4, dan 6 g/L. Semua parameter tersebut dihasilkan melalui analisa elemen terhingga (FEA) yang telah meramalkan sempadan perintis bagi prosedur halangan aglomerasi serbuk semasa pemesinan EDM. Penimbang digital, pengukur kekasaran permukaan (SJ400 Mitutoyo), pengukur kekerasan permukaan (Shimadzu Vickers's tester), dan mikroskop pengimbasan elektron-spektroskopi penyebaran tenaga X-ray (Hitachi SU-1510) telah digunakan dalam menentukan kadar penyingkiran bahan (MRR), kadar kehausan perkakas (TWR), purata kekasaran permukaan (R_a), kekerasan permukaan mikro (MH), ketebalan lapisan tuangan permukaan (RLT), dan peratus aglomerasi (%AG) selepas proses pemesinan. Bergantung kepada pemerhatian ke atas permukaan sebelum dan selepas pemesinan menggunakan spektroskopi penyebaran tenaga X-ray (EDS), peratusan berat elemen kromium telah berubah daripada 7.78% kepada 3.12% dan 6.68%. Lantaran, zarah NCP tidak berjaya teraglomerasi di zon jurang antara-elektrod. Tambahan pula, pengaglomerasian karbon dan unsur-unsur lain juga menyumbang dalam meningkatkan kekerasan permukaan mikro dari 655 hingga 675 HV ke 784 hingga 911.65 HV. Penggunaan teknik pengoptimuman hibrid RSM-ANOVA-TOPSIS telah berjaya menggalakan keinginan komposit dalam teknik pengoptimuman respon pelbagai (MRO) yang dihasilkan oleh RSM dari 0.6153 hingga 0.9997. Tambahan pula, teknik hibrid ini telah berjaya menetapkan nilai $I_p = 10$ Amps, $T_{on} = 30 \mu s$, dan $P_C = 2$ g/L sebagai parameter optimum, manakala $I_p = 20$ Amps, $T_{on} = 20 \mu s$, dan $P_C = 6$ g/L sebagai parameter terendah. Dengan itu, kos ramalan daripada parameter optimum telah menurun sebanyak 40.23% berbanding dengan parameter terendah.

CONTENT

TITLE	ii
DECLARATION	iii
DEDICATION	iv
ACKNOWLEDGEMENT	v
ABSTRACT	vi
ABSTRAK	vii
CONTENT	viii
LIST OF TABLES	xiv
LIST OF FIGURES	xx
LIST OF ABBREVIATIONS AND SYMBOLS	xxxvii
LIST OF APPENDICES	xliv
 CHAPTER 1 INTRODUCTION	 1
1.1 Introduction	1
1.2 Machining of AISI D2 steel by conventional machines	1

1.3	Machining of AISI D2 steel by Electrical Discharge	
	Discharge Machining (EDM)	2
1.3.1	Machining of AISI D2 steel in powder	
	Mixed-EDM (PMEDM)	4
1.4	Problem statement	5
1.5	Research objectives	7
1.6	Scope of the study	8
1.7	Significance of the study	9
1.8	Thesis organisation	10
	CHAPTER 2 LITERATURE REVIEW	12
2.1	Introduction	12
2.2	PMEDM background	13
2.3	Review on performance obstacles in PMEDM	26
	2.3.1 Review on MRR obstacles	26
	2.3.1.1 Summary and interpretations	36
	2.3.2 Review on TWR obstacles	38
	2.3.2.1 Summary and interpretations	42
	2.3.3 Review on surface quality obstacles	43
	2.3.3.1 Summary and interpretations	58
	2.3.4 Review on microhardness performance	59

2.3.4.1	Summary and interpretations	64
2.4	Review work	67
2.5	Numerical model of erosion operation	80
2.5.1	Spark (plasma) radius	83
2.6	Governing equation of plasma channel domain	84
2.7	Review on numerical analysis in PMEDM	88
2.7.1	Limitations of heat flux model	95
2.8	Validation environment and pilot procedures	97
2.9	Experimental design in PMEDM	107
2.10	Summary of literature review	112
CHAPTER 3 RESEARCH METHODOLOGY		116
3.1	Introduction	116
3.2	Research procedures	118
3.2.1	Work materials preparation	118
3.2.2	Setup parameters and experimental design	121
3.2.3	Experimental environment	124
3.3	Machinability responses and instrument	124
3.3.1	Material removal rate (MRR)	125
3.3.2	Tool wear rate (TWR)	126
3.3.3	Average of surface roughness (R_a)	126

3.4	Surface integrity responses and measurement	128
3.4.1	Microhardness (MH)	128
3.4.2	Recast layer thickness (RLT)	130
3.4.3	Agglomeration ratio (%AG)	131
3.5	Remarks concerning by workpiece preparing	135
3.6	Optimization	140
3.6.1	Single and multiple-response optimization	141
3.6.2	Pure and hybrid optimization	143
3.7	Summary of research methodology	148

CHAPTER 4 EXPERIMENTAL OUTCOMES AND INTERPRETATIONS OF MACHINABILITY AND SURFACE INTEGRITY

4.1	Introduction	152
4.2	Machinability performance	153
4.2.1	Material removal rate of AISI D2 hardened steel	153
4.2.2	Tool wear rate of copper electrode	169
4.2.3	Average roughness of machining zone in AISI D2 steel	186
4.2.4	Behavior machinability in central points	200

4.2.5	Numerical prediction of MRR and R_a in PMEDM	203
4.2.6	Overlays of the machinability responses in PMEDM	211
4.2.7	Summary of evaluation of the machinability performance in PMEDM	215
4.3	Surface integrity performance	220
4.3.1	Recast Layer Thickness (RLT) of machined zone	221
4.3.2	Microhardness (MH) of recast layer zone	236
4.3.3	Performance of agglomeration	248
4.3.4	Performance of central points	265
4.3.5	Relation between traditional responses and agglomeration	268
4.3.6	Overlays of the surface integrity responses in PMEDM	272
4.3.7	Summary of evaluation of the surface integrity performance in PMEDM	276
4.4	Optimization performance	281
4.4.1	Summary of optimization performance	293

CHAPTER 5 CONCLUSION & RECOMMENDATION	299
5.1 Conclusions	299
5.2 Main contributions	306
5.3 Recommendations of the future work	307
GANTT CHART FOR RESEARCH	309
RELATED & CONTRIBUTED PUBLISHING WITH	312
RELATED WORKSHOPS & CONFERENCES	
REFERENCES	341
APPENDICES	371



LIST OF TABLES

2.1	Chemical composition for die steel used in PMEDM before and after machining (Kumar and Batra, 2012).	60
2.2	Active elements of some sample after machining in PMEDM system that observed by EDX, EDS, and OES.	74
2.3	Significant observations related to work materials in the PMEDM environment..	75
2.4	Behaviour observations based on significant studies applied on AISI D2 in PMEDM.	76
2.5	Zingerman's equations that are construed the heat source of plasma channel.	80
2.6	Studies adopted Zingerman's equations in the electrical erosion.	80
2.7	Responses performed in EDM and PMEDM environments.	90
2.8	Properties of workpiece used in verification and validation.	99
2.9	Thermal properties of workpiece used in verification and validation.	99
2.10	Verification performed in this study with (Kumar <i>et al.</i> , 2014).	100
2.11	Validation performed in this study with Abrol and Sharma (2015) based on study of Kansal <i>et al.</i> (2008).	102

2.12	Validation performed in this study with Abrol and Sharma (2015) based on study of Abbas and Lajis (2018).	102
2.13	Survey of PMEDM studies that adopted the TOPSIS technique.	112
2.14	Comparison amongst outputs based on the observations of the literature review and challenges adopted in this study. Observed; the experimental conditions adopted in the present study and the targets.	115
3.1	Thermo-physical Properties of work materials (Lajis and Hosni, 2018; Ahmad, 2016; MakeItFrom, 2009).	120
3.2	Typical chemical composition of the workpiece and additive powder (refer Appendices E and F).	120
3.3	Experimental conditions on PMEDM for machining AISI D2 steel.	121
3.4	Experimental design and the PMEDM's responses.	122
3.5	Weight percentage of elements and microhardness ranges for D2 steel before machining in PMEDM.	139
3.6	Pairwise comparisons scale criteria (Saaty, 1990; Brunelli, 2014).	144
4.1	Outcomes of MRR for AISI D2 hardened steel in PMEDM.	154
4.2	Analysis of variance of MRR of AISI D2 steel before elimination stage.	162
4.3	Analysis of variance of MRR of AISI D2 steel after elimination stage.	164
4.4	Contribution of parameters in MRR based on F-Value.	164
4.5	Comparison between experimental results of MRR and fitting before and after elimination stages.	165
4.6	Outcomes of TWR for the copper electrode in PMEDM.	169

4.7	Summarizes the values of the damage-sensing constant for the electrode depending on pulse duration.	171
4.8	Analysis of variance of TWR of AISI D2 steel before elimination stage	180
4.9	Analysis of variance of TWR of AISI D2 steel after elimination stage.	181
4.10	Contribution of parameters in TWR based F-Value.	182
4.11	Comparison between experimental results of TWR and fitting before and after elimination stages.	183
4.12	Outcomes of R_a for the AISI D2 Steel in PMEDM.	190
4.13	Analysis of variance of R_a of AISI D2 steel before elimination stage.	193
4.14	Analysis of variance of R_a of AISI D2 steel after elimination stage.	194
4.15	Contribution of parameters in R_a based F-Value.	195
4.16	Comparison between experimental results of R_a and fitting before and after elimination stages.	198
4.17	Replication cases with error percentage for MRR, TWR, and R_a in PMEDM.	201
4.18	Replication central cases with error percentage for MRR, TWR, and R_a in PMEDM.	202
4.19	Numerical investigated of MRR and R_a of AISI D2 steel resulted by PMEDM.	204
4.20	Maximum and minimum ranges of MRR, TWR, and R_a responses in the machinability of AISI D2 steel by using copper electrode and NCP in PMEDM environment at interacted case ($I_p \times T_{on}$).	212
4.21	Overlay limitation equations for MRR, TWR, and R_a at central points.	215

4.22	Best parameters employed in the machinability of AISI D2 hardened steel in the PMEDM environment.	218
4.23	Results of RLT of machined zone for AISI D2 hardened steel in the PMEDM.	221
4.24	Analysis of variance for average of RLT before elimination stage.	230
4.25	Analysis of variance for average of RLT after elimination stage.	231
4.26	Comparison between experimental results of average RLT and fitting before and after elimination stages.	233
4.27	Contribution of parameters in average RLT based and F-Value.	236
4.28	Results of MH of machined zone for AISI D2 hardened steel.	237
4.29	Analysis of variance for average of MH before elimination stage.	243
4.30	Analysis of variance for average of MH after elimination stage.	244
4.31	Comparison between experimental results of average MH and fitting before and after elimination stages.	245
4.32	Contribution of parameters in average MH based and F-Value.	246
4.33	Weights percentages for AISI D2 hardened steel elements after machining stage in the PMEDM performed by EDS observations.	249
4.34	Atomics weights for AISI D2 hardened steel elements after machining stage in the PMEDM performed by EDS observations.	250
4.35	Results of %AG for the machined zone of AISI D2	253

	hardened steel.	
4.36	Analysis of variance for %AG before elimination stage.	254
4.37	Analysis of variance for %AG after elimination stage.	255
4.38	Comparison between experimental results of %AG and fitting before and after elimination stages.	256
4.39	Contribution of parameters in %AG based and F-Value.	257
4.40	Replication cases with error percentage for RLT, MH, and %AG in PMEDM.	265
4.41	Replication central cases with error percentage for RLT, MH, and %AG in PMEDM.	266
4.42	Maximum and minimum ranges of RLT, MH, and %AG responses for the surface integrity of AISI D2 steel by using copper electrode and NCP in PMEDM environment at interacted case ($I_p \times T_{on}$).	273
4.43	Overlay limitation equations for MRR, TWR, and R_a at central points.	275
4.44	Best parameters employed in the surface integrity for machined zone of AISI D2 hardened steel in the PMEDM environment.	279
4.45	Confirmation test and comparison with outcomes of machinability responses.	284
4.46	Confirmation test and comparison with outcomes of surface integrity responses.	285
4.47	Multiple-Response Optimization (MRO) for the performance of machinability and surface integrity responses.	285
4.48	Normalized decision matrix for responses of machining AISI D2 hardened steel and modifying the machined surface in PMEDM environment.	286

4.49	Criterion values of PCS for machinability and surface integrity responses according to AHP method.	287
4.50	Weight factors of machinability and surface integrity depending on Entropy, AHP, and TOPSIS.	287
4.51	Normalized weight matrix of machinability and surface integrity responses according to TOPSIS technique.	288
4.52	Positive and negative ideal solutions with RCIS values and ranking of machinability and surface integrity responses.	289
4.53	ANOVA of the RCIS-Multifunction for the hybrid optimization.	290
4.54	Performance comparison and the incremental between optimum and worst cases for machinability and surface integrity responses.	292
5.1	OLE models of the feasible performance at central points designated for the machinability and surface integrity responses in PMEDM.	303
5.2	Ranges of error percentages for outcomes of machinability and surface integrity responses at corners and central points designated.	304
5.3	Average of error percentages between the experimental and FEA-Numerical outcomes of MRR and R_a .	304
5.4	Single-Optimization performance with confirmation and error percentage for each response in PMEDM.	304
5.5	Multiple-Response Optimization performance of the machinability and surface integrity responses in the PMEDM.	305

LIST OF FIGURES

2.1	Wear results according to (Miyazaki <i>et al.</i> , 1995).	14
2.2	EDM environment with mixed container: (1) Fixture; (2) Workpiece; (3) Electrode tool; (4) Holding with dial; (5) Nozzle; (6) Pure kerosene in original container; (7) Stirrer; (8) Outer container; (9) Mixed dielectric Fluid; (10) Filter; (11) Pump (Ming and He, 1995).	14
2.3	EDM environment to mixed powder with dielectric fluid according to (Wong <i>et al.</i> , 1998).	15
2.4	Comparison of microstructure between pure EDM and mixed powder dielectric fluid. Observed: (a) Pure EDM; (b) at 2 g/L of graphite powder mixed; (c) at 2 g/L of silicon powder mixed (Wong <i>et al.</i> , 1998).	15
2.5	Reciprocating motion of the powder particles between electrodes in the dielectric fluid according to (Furutania <i>et al.</i> , 2001).	16
2.6	Texture of the machining surface of AISI H13: An electrode area 32 cm ² (a) Pure EDM and (b) Mixed silicon (Si) powder; An electrode area 64 cm ² (c) Pure EDM and (d) Mixed silicon (Si) powder (Pecas and Henriques, 2003).	17
2.7	Integrated system with EDM machine according to (Klocke <i>et al.</i> , 2004).	18

2.8	Comparison between the expanding of the spark in pure and mixed dielectric fluid observed by High-Speed Frame Camera (HSFC), where: (a) Pure dielectric fluid; (b) mixed dielectric fluid with Silicon; (c) mixed dielectric fluid with Aluminium (Klocke <i>et al.</i> , 2004).	19
2.9	Integrated EDM environment (Tzeng and Lee, 2001; Tzeng and Chen, 2005)	19
2.10	Comparison average surface roughness (R_a) and recast layer of pure and mixed dielectric fluid. Observed in (a) R_a Performance in pure or different mixed powders; (b) Recast layer performance in pure or different mixed dielectric fluid (Tzeng and Chen, 2005).	20
2.11	Schematic of PMEDM environment used by (Kansal <i>et al.</i> , 2005).	21
2.12	PMEDM environment proposed by (Kansal <i>et al.</i> , 2007a).	22
2.13	Topography of machined surface for AISI H13 by SEM, where observed (a) Pure EDM; (b) 1 g/L of silicon powder in PMEDM; (c) 2 g/L of silicon powder in PMEDM; (d) 20 g/L of silicon powder in PMEDM (Peças and Henriques, 2008).	23
2.14	RLT of machined surface of AISI H13. Observed the RLT at (a) Pure EDM; (b) at 2 g/L of silicon powder; (c) at 20 g/L of silicon powder (Peças and Henriques, 2008).	24
2.15	Effect of concentration of Aluminium powder on the machinability of Hastelloy steel (Sharma <i>et al.</i> , 2010).	25
2.16	Influence of powder concentration on MRR based on the type of powder (Jabbaripour <i>et al.</i> , 2013).	27
2.17	Influence of amount of boron carbide (B_4C) powder on	28

	the performance of MRR (Kolli and Kumar, 2014).	
2.18	Effect of carbon nanotubes (CNTs) concentration on MRR of AISI D2 steel (Kumar, 2015).	29
2.19	Variation of MRR with the size and powder concentration. Observed (a) 110 V/220 pF; (b) 70 V/220 pF (Prihandana and Sriani, 2014).	30
2.20	Effect the concentration of Gr powder on MRR (Unses and Cogun, 2015).	31
2.21	Effect of powder concentration on the performance of the material removal rate according to outcomes (Baseri and Sadeghian, 2016).	32
2.22	Effect of pulse off-Time (T_{off}) and pulse on-Time (T_{on}) on the removal rate of D2 steel at variation or peak current (Marashi <i>et al.</i> , 2015).	33
2.23	Effect of types of dielectric fluids on MRR in PMEDM during machining Tungsten Carbide-Cobalt (WC-Co). Observed (a) Effect of pulse-on-time on MRR; (b) Effect of peak current on MRR (Singh and Sharma, 2016).	34
2.24	Effect of pulse duration on the removal rate of titanium alloy in EDM and PMEDM environments. Observed (a) Effect pulse duration on MRR at 12 Amps; (b) Effect pulse duration on MRR at 48 Amps (Shabgard and Khosrozadeh, 2017).	35
2.25	Agglomeration phenomenon between electrode tool and workpiece (Prihandana <i>et al.</i> , 2012; Prihandana and Sriani, 2014).	37
2.26	Effect of wear rate on (a) machining time and cutting depth; (b) Tungsten (W) particles accumulated on the machining zone at $P_C = 0.28$ g/L of CNF (Jun <i>et al.</i> ,	39

	2013).	
2.27	Effect of powder concentration on the performance of the tool wear rate according to outcomes (Baseri and Sadeghian, 2016).	40
2.28	Effect of pulse duration on the surface roughness of titanium alloy in EDM and PMEDM environments. Observed (a) Effect pulse duration on TWR at 24 Amps; (b) Effect pulse duration on TWR at 48 Amps (Shabgard and Khosrozadeh, 2017).	42
2.29	Comparison the recast layer thickness for machining surface of W300 steel at (a) $I_p = 6$ Amps, $P_C = 1$ g/L, $T_{on} = 180$ μ s, and negative polarity; (b) $I_p = 6$ Amps, $P_C = 1$ g/L, $T_{on} = 180$ μ s, and positive polarity (Syed and Palaniyandi, 2012).	44
2.30	Comparison the recast layer for titanium alloy resulted from machining in PMEDM. Observed (a) Minimum RLT at $I_p = 24$ Amps, $T_{on} = 12.8$ μ s, and $T_{off} = 50$ μ s; (b) Maximum RLT at $I_p = 24$ Amps, $T_{on} = 50$ μ s, and $T_{off} = 50$ μ s (Izman <i>et al.</i> , 2012).	45
2.31	Influence of carbon nanotubes (CNTs) concentration on the machining time and average surface roughness for NAK80 steel (Mai <i>et al.</i> , 2012).	46
2.32	Variation of RLT with pulse on-time and concentration of silicon carbide powder based on (a) 22 Amps; (b) 14 Amps; (c) 7 Amps (Ekmekci and Ersoz, 2012).	47
2.33	Optical cross-sectional for machined surface by PMEDM environment at $T_{on} = 400$ μ s and $I_p = 7$ Amps. Observed RLT at (a) 10 g/L of SiC Powder; (b) 15 g/L of SiC Powder (Ekmekci and Ersoz, 2012).	48
2.34	SEM-Morphology for machined surface by PMEDM	48

	environment at $T_{on} = 400 \mu s$ and $I_P = 7$ Amps. Observed morphology at (a) 5 g/L of SiC powder; (b) 15 g/L of SiC powder (Ekmekci and Ersoz, 2012).	
2.35	Influence of powder concentration on R_a based on the type of powder (Jabbaripour <i>et al.</i> , 2013).	49
2.36	Influence of concentration of boron carbide (B_4C) powder on the surface roughness (Kolli and Kumar, 2014).	50
2.37	Influence of carbon nanotubes (CNTs) concentration on R_a in D2 steel (Kumar, 2015).	51
2.38	Topography of titanium alloy machining in PMEDM at 2 Amps. Observed (a) at $T_{on} = 25 \mu s$; (b) at $T_{on} = 1600 \mu s$ (Yaşar and Ekmekci, 2014).	51
2.39	Influence of graphite powder concentration on R_a in PMEDM (Unses and Cogun, 2015).	52
2.40	Cross sectional for RLT producing from machining AISI H13 at $I_P = 2$ Amps in the PMEDM. Observed (a) RLT at concentration 5 g/L of silicon (Si) powder; (b) RLT at concentration 5 g/L of manganese (Mn) powder (Molinetti <i>et al.</i> , 2016).	53
2.41	Influence of energy and concentration of titanium dioxide (TiO_2) powder on the average surface roughness of AISI H13 steel (Baseri and Sadeghian, 2016).	54
2.42	Average surface roughness of titanium alloy and EDS analysis for machining sample at 45 μs and 150 μs for pulse off-time and pulse on-time, respectively. Noted the topography and EDS analysis (a) and (b) at 6 Amps, while (c) and (d) at 14 Amps (Kumar <i>et al.</i> , 2015b).	54
2.43	Average surface roughness of AISI D2 steel in PMEDM. Observed R_a at (a) $T_{on} = 120 \mu s$ and $T_{off} = 80 \mu s$; (b) $T_{on} = 210 \mu s$ and $T_{off} = 140 \mu s$; (c) $T_{on} = 340 \mu s$	55

	and $T_{off} = 225 \mu s$ (Marashi <i>et al.</i> , 2015).	
2.44	Influence of chromium powder concentration and discharge current on RLT and R_a for SKD11 steel (Toshimitsu <i>et al.</i> , 2016).	56
2.45	Effect of pulse duration on the surface roughness of titanium alloy in EDM and PMEDM environments. Observed (a) Effect pulse duration on R_a at 12 A; (b) Effect pulse duration on R_a at 48 A (Shabgard and Khosrozadeh, 2017).	57
2.46	Comparison microhardness in pure EDM and PMEDM for SiCp/Al and ASP-23 materials (Hu <i>et al.</i> , 2013).	61
2.47	Comparison microhardness for profile of AISI H13 machining by PMEDM environment. Observed (a) Machining with Silicon (Si) powder; (b) Machining with Manganese (Mn) powder (Molinetti <i>et al.</i> , 2016).	62
2.48	Cross-Sectional of machined surface for AISI H13 steel clarified the influence of the deposited powder on the performance of microhardness in PMEDM (Amorim <i>et al.</i> , 2017).	65
2.49	Wear mass of PMED as compared with other cases (Hu <i>et al.</i> , 2013).	65
2.50	Components of PMEDM environment (Kansal <i>et al.</i> , 2007a, 2007b).	67
2.51	Effect forces on the particle in the PMEDM (Jahan <i>et al.</i> , 2010).	68
2.52	Zig-Zag bridge resulted from mixed particle powder with dielectric liquid in EDM machine (Kumar, 2015).	69
2.53	Schematic interprets the agglomeration criterion with MRR and microhardness.	72
2.54	Schematic summary clarifies the reasons of the powder agglomeration case in PMEDM.	73

2.55	Schematic clarifies influence the peak current, pulse duration, and concentration of the additive powder in machining D2 steel in PMEDM environment.	78
2.56	Mechanism of plasma distribution in PMEDM and EDM environments based on Gaussian's distribution (Kansal <i>et al.</i> , 2008; Izquierdo <i>et al.</i> , 2009; Joshi and Pande, 2010).	83
2.57	Numerical validation for MRR of D2 steel in PMEDM environment (Kansal <i>et al.</i> , 2008).	89
2.58	Numerical validation for RLT and R_{\max} achieved by (Tan and Yeo, 2013).	89
2.59	Numerical validation for MRR of BeCu alloy in the PMEDM (Jatti and Bagane, 2018).	90
2.60	Proposed machining zones in PMEDM by (Kansal <i>et al.</i> , 2008).	91
2.61	Radius and depth of the crater resulted by EDM and PMEDM environments based on studying (Kansal <i>et al.</i> , 2008).	92
2.62	Proposed geometry of the crater by (Salonitis <i>et al.</i> , 2009).	93
2.63	Craters interaction based on understood (Salonitis <i>et al.</i> , 2009).	94
2.64	Validation MRR based on gap distance in PMEDM (Abbas and Lajis, 2018).	96
2.65	Steps of verification, validation, and pilot procedure using FEA to specify active parameters.	98
2.66	Verification with the experimental and numerical values for MRR of Inconel 718 according to study (Kumar <i>et al.</i> , 2014).	100
2.67	Verification model for crater during machining Inconel 718 in pure EDM at; $I_p = 11$ Amps, $T_{on} = 100 \mu s$, and V	101

REFERENCES

Abbas, M. A, Lajis, M. A. (2018) 'The Effect of the Gap Distance Between Electrodes on Removal Rate in PMEDM Using FEA', in *4th International Conference on Mechanical, Manufacturing and Plant Engineering*. Lecture Notes in Mechanical Engineering, pp. 1–10.

Abbas, M. A., Lajis, M. A. and Abdul Ridha, G. S. (2019) 'A New Methodology For Predicting Quantity Of Agglomeration Between Electrodes In PMEDM Environment', *International Journal of Mechanical Engineering and Technology*, 10(2), pp. 1461–1479.

Abbas, M. A, Lajis, M. A., Jawad, A. D, Rahim. E. A *et al.* (2019) 'Influence of the spark heat on the electrode behavior in Powder Mixed-EDM environment', *Journal of Mechanical Engineering and Sciences*, 13(4) pp. 510–517. doi: 10.15282/jmes.13.4.2019.25.04.

Abdul-Rani, A. M. *et al.* (2017) 'Machined surface quality in nano aluminum mixed electrical discharge machining', in *International Conference on Sustainable Materials Processing and Manufacturing*. Elsevier, pp. 6125–6143. doi: 10.1016/j.promfg.2016.12.061.

Abrol, A. and Sharma, S. (2015) 'Effect of Chromium Powder Mixed Dielectric on Performance Characteristic of Aisi D2 Die Steel Using EDM', *International Journal of Research in Engineering and Technology*, 4(1), pp. 232–246. doi: <https://doi.org/10.15623/ijret.2015.0401036>.

Ahmad, S. (2016) *Improvement of Machinability and Surface Integrity During Electro Discharge Machining of Inconel 718 Using Nano Power Suspension Dielectric*. Universiti Tun Hussein Onn Malaysia.

Ahmad, S. *et al.* (2018) 'Surface Roughness and Surface Topography of Inconel 718 in Powder Mixed Dielectric Electrical Discharge Machining (PMEDM)', *International Journal of Integrated Engineering*, 10(5). doi: 10.30880/ijie.2018.10.05.027.

Ajay Batish, Anirban Bhattacharya, V. K. Singla and Singh, G. (2012) 'Study of Material Transfer Mechanism in Die Steels Using Powder Mixed Electric Discharge Machining', *Materials and Manufacturing Processes*, 27(June 2017), pp. 449–456. doi: 10.1080/10426914.2011.585498.

Al-Khazraji, A., Amin, S. A. and Ali, S. M. (2016) 'The effect of SiC powder mixing electrical discharge machining on white layer thickness, heat flux and fatigue life of AISI D2 die steel', *Engineering science and technology, an international journal*. Elsevier, 19(3), pp. 1400–1415. doi: <https://doi.org/10.1016/j.jestch.2016.01.014>.

Algodí, S. J., Clare, A. T. and Brown, P. D. (2018) 'Modelling of single spark interactions during electrical discharge coating', *Journal of Materials Processing Technology*. Elsevier, 252, pp. 760–772. doi: 10.1016/j.jmatprotec.2017.10.029.

Amorim, F. L. *et al.* (2017) 'Surface modification of tool steel by electrical discharge machining with molybdenum powder mixed in dielectric fluid', *The International Journal of Advanced Manufacturing Technology*. Springer, 91(1–4), pp. 341–350. doi: 10.1007/s00170-016-9678-x.

Anirban Bhattacharya, Ajay Batish, Gurmail Singh, and Singla, V. K. (2012) 'Optimal parameter settings for rough and finish machining of die steels in powder-mixed EDM', *The International Journal of Advanced Manufacturing Technology*, 61(5–8), pp. 537–548. doi: 10.1007/s00170-011-3716-5.

Arsecularatne, J. A. *et al.* (2006) 'On machining of hardened AISI D2 steel with PCBN tools', *Journal of Materials Processing Technology*. Elsevier, 171(2), pp. 244–252. doi: <https://doi.org/10.1016/j.jmatprotec.2005.06.079>.

Assarzadeh, S. and Ghoreishi, M. (2013) 'A dual response surface-desirability approach to process modeling and optimization of Al₂O₃ powder-mixed electrical discharge machining (PMEDM) parameters', *The International Journal of Advanced Manufacturing Technology*. Springer, 64(9–12), pp. 1459–1477. doi: 10.1007/s00170-012-4115-2.

Bagchi, S. N. and Prakash, K. (1986) *Industrial Steel Reference Book*. Revised Se. New Age International Pub. (P) Limited.

Bains, P. S. *et al.* (2019) 'Magnetic field influence on surface modifications in powder mixed EDM', *Silicon*. Springer, 11(1), pp. 415–423. doi: 10.1007/s12633-018-9907-z.

Baseri, H. and Sadeghian, S. (2016) 'Effects of nanopowder TiO₂-mixed dielectric and rotary tool on EDM', *The International Journal of Advanced Manufacturing Technology*. Springer, 83(1–4), pp. 519–528. doi: <https://doi.org/10.1007/s00170-015-7579-z>.

Batish, A. and Bhattacharya, A. (2012) 'Mechanism of material deposition from powder , electrode and dielectric for surface modification of H11 and H13 die steels in EDM process', *Materials Science Forum*, 701, pp. 61–75. doi: 10.4028/www.scientific.net/MSF.701.61.

Batish, A., Bhattacharya, A. and Kumar, N. (2015) 'Powder mixed dielectric: an approach for improved process performance in EDM', *Particulate Science and Technology*. Taylor & Francis, 33(2), pp. 150–158. doi: 10.1080/02726351.2014.947659.

Beck, J. V (1981) 'Transient temperatures in a semi-infinite cylinder heated by a disk

heat source', *International Journal of Heat and Mass Transfer*. Elsevier, 24(10), pp. 1631–1640. doi: 10.1016/0017-9310(81)90071-5.

Bhatt, G., Batish, A. and Bhattacharya, A. (2015) 'Experimental investigation of magnetic field assisted powder mixed electric discharge machining', *Particulate Science and Technology*. Taylor & Francis, 33(3), pp. 246–256. doi: <https://doi.org/10.1080/02726351.2014.968303>.

Bhattacharya, A. *et al.* (2012) 'Optimal parameter settings for rough and finish machining of die steels in powder-mixed EDM', *The International Journal of Advanced Manufacturing Technology*. Springer, 61(5–8), pp. 537–548. doi: 10.1007/s00170-011-3716-5.

Bhattacharya, A. and Batish, A. (2012) 'Effect of process variables on microhardness, grain size and strain during machining of various die steels with powder-mixed electric-discharge machining using dummy treated experimental design', *Proceedings of the Institution of Mechanical Engineers, Part B: Journal of Engineering Manufacture*. Sage Publications Sage UK: London, England, 226(7), pp. 1192–1204. doi: 10.1177/0954405412442777.

Bhattacharya, A., Batish, A. and Kumar, N. (2013) 'Surface characterization and material migration during surface modification of die steels with silicon, graphite and tungsten powder in EDM process', *Journal of Mechanical Science and Technology*. Springer, 27(1), pp. 133–140. doi: 10.1007/s12206-012-0883-8.

Bhattacharya, A., Batish, A. and Singh, G. (2012) 'Optimization of powder mixed electric discharge machining using dummy treated experimental design with analytic hierarchy process', *Proceedings of the Institution of Mechanical Engineers, Part B: Journal of Engineering Manufacture*. Sage Publications Sage UK: London, England, 226(1), pp. 103–116. doi: 10.1177/0954405411402876.

Bhaumik, M. and Maity, K. (2017) 'Effect of machining parameter on the surface

roughness of AISI 304 in silicon carbide powder mixed EDM', *Decision Science Letters*, 6(3), pp. 261–268. doi: 10.5267/j.dsl.2016.12.004.

Bhaumik, M. and Maity, K. (2018) 'Experimental investigation and finite element simulation of AISI 304 during electro discharge machining', *International Journal of Modeling, Simulation, and Scientific Computing*. World Scientific, 9(04), p. 1850022.

Bhushan, B. (2002) 'Introduction to Tribology', in. Wiley, pp. 18–21. Available at: <https://books.google.com.my/books?id=U9er18cvVeEC>.

Bhuyan, R. K., Routara, B. C. and Parida, A. K. (2015) 'An approach for optimization the process parameter by using TOPSIS Method of Al--24% SiC metal matrix composite during EDM', in *Materials Today: Proceedings: 4th International Conference on Materials Processing and Characterization*. Elsevier, pp. 3116–3124. doi: 10.1016/j.matpr.2015.07.272.

Boopathi, R. and Sundaram, S. (2014) 'Influence of Process Parameters for Electrical Discharge Machine Using Nano Particle and Brass Electrode', *International Journal of Research in Advent Technology*. Citeseer, 2(11).

Bose, Gk. and Mahapatra, Kk. (2014) 'Parametric study of die sinking EDM process on AISI H13 tool steel using statistical techniques.', *Advances in Production Engineering & Management*, 9(4). doi: 10.14743/apem2014.4.185.

Brunelli, M. (2014) *Introduction to the analytic hierarchy process*. Springer.

Bryson, W. E. (2009) 'Heat Treatment, Selection, and Application of Tool Steels', in. Hanser, pp. 181–204. Available at: <https://books.google.com.my/books?id=ZYtTewAACAAJ>.

Bulent Ekmekci and Yusuf Ersoz (2012) 'How Suspended Particles Affect Surface Morphology in Powder Mixed Electrical Discharge Machining (PMEDM)',

Metallurgical and Materials Transactions B, 43(5), pp. 1138–1148. doi: 10.1007/s11663-012-9700-0.

Çaliskan, H. *et al.* (2013) ‘Material selection for the tool holder working under hard milling conditions using different multi criteria decision making methods’, *Materials & Design*. Elsevier, 45, pp. 473–479. doi: 10.1016/j.matdes.2012.09.042.

Del Castillo, E., Montgomery, D. C. and McCarville, D. R. (1996) ‘Modified desirability functions for multiple response optimization’, *Journal of quality technology*. Taylor & Francis, 28(3), pp. 337–345. doi: 10.1080/00224065.1996.11979684.

Chakraborty, S., Dey, V. and Ghosh, S. K. (2015) ‘A review on the use of dielectric fluids and their effects in electrical discharge machining characteristics’, *Precision Engineering*. Elsevier, 40, pp. 1–6. doi: 10.1016/j.precisioneng.2014.11.003.

Chaudhury, P., Samantaray, S. and Sahu, S. (2017b) ‘Multi Response Optimization of Powder Additive Mixed Electrical Discharge Machining by Taguchi Analysis’, in *5th International Conference of Materials Processing and Characterization (ICMPC 2016)*. Elsevier Ltd, pp. 2231–2241. doi: <https://doi.org/10.1016/j.matpr.2017.02.070>.

Coldwell, H. *et al.* (2003) ‘Rapid machining of hardened AISI H13 and D2 moulds, dies and press tools’, *Journal of materials processing technology*. Elsevier, 135(2), pp. 301–311. doi: [https://doi.org/10.1016/s0924-0136\(02\)00861-0](https://doi.org/10.1016/s0924-0136(02)00861-0).

Czelusniak, T. *et al.* (2019) ‘Materials used for sinking EDM electrodes: a review’, *Journal of the Brazilian Society of Mechanical Sciences and Engineering*. Springer, 41(1), p. 14. doi: 10.1007/s40430-018-1520-y.

D’Urso, G., Quarto, M. and Ravasio, C. (2017) ‘A model to predict manufacturing cost for micro-EDM drilling’, *The International Journal of Advanced Manufacturing Technology*. Springer, 91(5–8), pp. 2843–2853. doi: 10.1007/s00170-016-9950-0.

Davis, J. R. and Committee, A. S. (2004) 'Handbook of Thermal Spray Technology', in. ASM International, p. 233. Available at: <https://books.google.com.my/books?id=S0PryYc9T70C>.

Descocudres, A. *et al.* (2005) 'Time-resolved imaging and spatially-resolved spectroscopy of electrical discharge machining plasma', *Journal of Physics D: Applied Physics*. IOP Publishing, 38(22), p. 4066. doi: 10.1088/0022-3727/38/22/009.

DiBitonto, D. D. *et al.* (1989) 'Theoretical models of the electrical discharge machining process. I. A simple cathode erosion model', *Journal of applied physics*. AIP, 66(9), pp. 4095–4103. doi: 10.1063/1.343994.

Van Dijck, F. S. and Dutre, W. L. (1974) 'Heat conduction model for the calculation of the volume of molten metal in electric discharges', *Journal of Physics D: Applied Physics*. IOP Publishing, 7(6), p. 899. doi: 10.1088/0022-3727/7/6/316.

Dwivedi, A. P. and Choudhury, S. K. (2017) 'Estimation of Recast Layer Thickness in Rotary Tool EDM Process for Machining AISI D3 Tool Steel', *Materials Today: Proceedings*. Elsevier, 4(10), pp. 10816–10822. doi: 10.1016/j.matpr.2017.08.033.

Erden, A. (1983) 'Effect of Materials on the Mechanism of Electric Discharge Machining', *Journal of Engineering Materials and Technology*, 105(2), pp. 132–138. doi: <https://doi.org/10.1115/1.3225627>.

Erden, A. and Bilgin, S. (1981) 'Role of impurities in electric discharge machining', in *Proceedings of the Twenty-First International Machine Tool Design and Research Conference*, pp. 345–350. doi: 10.1007/978-1-349-05861-7_45.

Erik Oberg, Franklin D. Jones, Holbrook L. Horton, A. H. H. R. (2016) 'Machinery' s Handbook, 30 th Edition', in. South Norwalk, U.S.A.: INDUSTRIAL PRESS, INC., pp. 420–429.

Furutani, K., Sato, H. and Suzuki, M. (2009) 'Influence of electrical conditions on performance of electrical discharge machining with powder suspended in working oil for titanium carbide deposition process', *The International Journal of Advanced Manufacturing Technology*. Springer, 40(11–12), pp. 1093–1101. doi: 10.1007/s00170-008-1420-x.

Furutania, K. *et al.* (2001) 'Accretion of titanium carbide by electrical discharge machining with powder suspended in working fluid', *Precision Engineering*. Elsevier, 25(2), pp. 138–144. doi: 10.1016/S0141-6359(00)00068-4.

Gaitonde, V. N. *et al.* (2009a) 'Analysis of machinability during hard turning of cold work tool steel (type: AISI D2)', *Materials and Manufacturing Processes*. Taylor & Francis, 24(12), pp. 1373–1382.

Gaitonde, V. N. *et al.* (2009b) 'Machinability investigations in hard turning of AISI D2 cold work tool steel with conventional and wiper ceramic inserts', *International Journal of Refractory Metals and Hard Materials*. Elsevier, 27(4), pp. 754–763.

Geels, K. (2006) 'Metallographic and Materialographic Specimen Preparation, Light Microscopy, Image Analysis, and Hardness Testing', in. ASTM International, pp. 100–102. Available at: <https://books.google.com.my/books?id=oaehZy3Vo1kC>.

Guu, Y. H. *et al.* (2003) 'Effect of electrical discharge machining on surface characteristics and machining damage of AISI D2 tool steel', *Materials Science and Engineering: A*. Elsevier, 358(1), pp. 37–43. doi: [https://doi.org/10.1016/S0921-5093\(03\)00272-7](https://doi.org/10.1016/S0921-5093(03)00272-7).

Guu, Y. H. (2005) 'AFM surface imaging of AISI D2 tool steel machined by the EDM process', *Applied Surface Science*. Elsevier, 242(3), pp. 245–250. doi: 10.1016/j.apsusc.2004.08.028.

Guu, Y. H. and Hocheng, H. (2001) 'Improvement of fatigue life of electrical discharge

machined AISI D2 tool steel by TiN coating', *Materials Science and Engineering: A*. Elsevier, 318(1), pp. 155–162.

Hosni, N. A. J. and Lajis, M. A. (2019) 'Multi-response optimization of the machining characteristics in electrical discharge machining (EDM) using span-20 surfactant and chromium (Cr) powder mixed', *Materialwissenschaft und Werkstofftechnik*. Wiley Online Library, 50(3), pp. 329–335. doi: 10.1002/mawe.201800204.

Hosseini Kalajahi, M., Rash Ahmadi, S. and Nadimi Babil Oliaei, S. (2013) 'Experimental and finite element analysis of EDM process and investigation of material removal rate by response surface methodology', *The International Journal of Advanced Manufacturing Technology*, 69(1–4), pp. 687–704. doi: <https://doi.org/10.1007/s00170-013-5059-x>.

Hu, F. Q. *et al.* (2013) 'Surface properties of SiCp / Al composite by powder-mixed EDM', in *The Seventeenth CIRP Conference on Electro Physical and Chemical Machining (ISEM)*, pp. 101–106. doi: 10.1016/j.procir.2013.03.036.

Ikai, T., Fujita, I. and Hashiguchi, K. (1992) 'Heat input radius for crater formation in the electric discharge machining', *IEEE Transactions on Industry Applications*. The Institute of Electrical Engineers of Japan, 112(10), pp. 943–949. doi: 10.1541/ieejias.112.943.

'Istfa 2005: Proceedings of the 31st International Symposium for Testing and Failure Analysis' (2005) in. A S M International (ISTFA. PROCEEDINGS), p. XXV. Available at: <https://books.google.com.my/books?id=TyjKhU3gWnoC>.

Izman, S. *et al.* (2012) 'Effects of adding multiwalled carbon nanotube into dielectric when EDMing titanium alloy', in *Advanced Materials Research*, pp. 1445–1449. doi: 10.4028/www.scientific.net/AMR.463-464.1445.

Izquierdo, B. *et al.* (2009) 'A numerical model of the EDM process considering the

effect of multiple discharges', *International Journal of Machine Tools and Manufacture*. Elsevier, 49(3), pp. 220–229. doi: 10.1016/j.ijmachtools.2008.11.003.

Jabbaripour, B., Hossein, M., *et al.* (2013) 'Investigating surface roughness , material removal rate and corrosion resistance in PMEDM of Gamma -TiAl intermetallic', *Journal of Manufacturing Processes*. The Society of Manufacturing Engineers, 15(1), pp. 56–68. doi: 10.1016/j.jmapro.2012.09.016.

Jagdeep SINGH, R. K. S. and Assessing (2016) 'Assessing the effects of different dielectrics on environmentally conscious powder-mixed EDM of dif fi cult-to- machine material (WC-Co)', *Frontiers of Mechanical Engineering*, 11(4), pp. 374–387. doi: 10.1007/s11465-016-0388-8.

Jahan, M. P., Rahman, M. and San Wong, Y. (2011) 'Study on the nano-powder-mixed sinking and milling micro-EDM of WC-Co', *The International Journal of Advanced Manufacturing Technology*. Springer, 53(1–4), pp. 167–180. doi: 10.1007/s00170-010-2826-9.

Jahan, M. P., Rahman, M. and Wong, Y. S. (2010) 'Modelling and experimental investigation on the effect of nanopowder-mixed dielectric in micro-electrodischarge machining of tungsten carbide', *Proceedings of the Institution of Mechanical Engineers, Part B: Journal of Engineering Manufacture*. Sage Publications Sage UK: London, England, 224(11), pp. 1725–1739. doi: 10.1243/09544054jem1878.

Jatti, V. S. and Bagane, S. (2018) 'Thermo-electric modelling, simulation and experimental validation of powder mixed electric discharge machining (PMEDM) of BeCu alloys', *Alexandria Engineering Journal*. Elsevier, 57(2), pp. 643–653. doi: <https://doi.org/10.1016/j.aej.2017.02.023>.

Jilani, S. T. and Pandey, P. C. (1982) 'Analysis and modelling of EDM parameters', *Precision Engineering*. Elsevier, 4(4), pp. 215–221. doi: 10.1016/0141-6359(82)90011-3.

Jilani, S. T. and Pandey, P. C. (1983) 'An analysis of surface erosion in electrical discharge machining', *Wear*. Elsevier, 84(3), pp. 275–284. doi: 10.1016/0043-1648(83)90269-7.

Joshi, S. N. and Pande, S. S. (2010) 'Thermo-physical modeling of die-sinking EDM process', *Journal of manufacturing processes*. Elsevier, 12(1), pp. 45–56. doi: <https://doi.org/10.1016/j.jmapro.2010.02.001>.

Jun, P., Yan, J. and Kuriyagawa, T. (2013) 'Carbon nanofiber assisted micro electro discharge machining of reaction-bonded silicon carbide', *Journal of Materials Processing Tech.* Elsevier B.V., 213(7), pp. 1076–1087. doi: 10.1016/j.jmatprotec.2013.02.004.

Juneja, B. L. and Seth, N. (2003) 'Fundamentals of Metal Cutting and Machine Tools', in. New Age International Publishers, pp. 278–279.

Kaintz, A. *et al.* (2013) 'Solute diffusion in ionic liquids, NMR measurements and comparisons to conventional solvents', *The Journal of Physical Chemistry B*. ACS Publications, 117(39), pp. 11697–11708.

Kaldhone, S. Y., Kavade, M. V and Rawat, U. (2014) 'Effect of powder mixed dielectric on performance measures of EDM for tungsten carbide', *International Journal of Innovative Research in Advanced Engineering*, 1(10), pp. 106–111.

Kansal, H. K., Singh, S. and Kumar, P. (2005) 'Parametric optimization of powder mixed electrical discharge machining by response surface methodology', *Journal of materials processing technology*. Elsevier, 169(3), pp. 427–436. doi: <https://doi.org/10.1016/j.jmatprotec.2005.03.028>.

Kansal, H. K., Singh, S. and Kumar, Pradeep (2006a) 'Performance parameters optimization (multi-characteristics) of powder mixed electric discharge machining (PMEDM) through Taguchi's method and utility concept', *Indian Journal of*

Engineering & Materials Sciences. CSIR, 13, pp. 209–216.

Kansal, H. K., Singh, S. and Kumar, P (2006b) ‘Performance parameters optimization of powder mixed electric-discharge machining (PMEDM) by Taguchi method’, *West Indian Journal of Engineering*, 29(1), pp. 81–94.

Kansal, H. K., Singh, S. and Kumar, P. (2007a) ‘Effect of silicon powder mixed EDM on machining rate of AISI D2 die steel’, *Journal of Manufacturing processes*. Elsevier, 9(1), pp. 13–22. doi: 10.1016/s1526-6125(07)70104-4.

Kansal, H. K., Singh, S. and Kumar, P. (2007b) ‘Technology and research developments in powder mixed electric discharge machining (PMEDM)’, *Journal of materials processing technology*. Elsevier, 184(1–3), pp. 32–41. doi: 10.1016/j.jmatprotec.2006.10.046.

Kansal, H. K., Singh, S. and Kumar, P. (2008) ‘Numerical simulation of powder mixed electric discharge machining (PMEDM) using finite element method’, *Mathematical and Computer Modelling*, 47(11–12), pp. 1217–1237. doi: 10.1016/j.mcm.2007.05.016.

Khan, A. A. (2011) ‘Role of heat transfer on process characteristics during electrical discharge machining’, in *Developments in Heat Transfer*. InTech. doi: 10.5772/21090.

Khan, A. A. *et al.* (2017) ‘Improvement of surface quality using silicon carbide powder added dielectric fluid during EDM’, in *IOP Conference Series: Materials Science and Engineering*, p. 12039. doi: 10.1088/1757-899X/184/1/012039.

Khosrozadeh, B. and Shabgard, M. (2017) ‘Effects of hybrid electrical discharge machining processes on surface integrity and residual stresses of Ti-6Al-4V titanium alloy’, *The International Journal of Advanced Manufacturing Technology*. Springer, 93(5–8), pp. 1999–2011. doi: 10.1007/s00170-017-0601-x.

Klocke, F. *et al.* (2004) ‘The effects of powder suspended dielectrics on the thermal

influenced zone by electrodischarge machining with small discharge energies', *Journal of materials processing technology*. Elsevier, 149(1–3), pp. 191–197. doi: 10.1016/j.jmatprotec.2003.10.036.

Knight, W. A. and Boothroyd, G. (2005) 'Fundamentals of Metal Machining and Machine Tools, Third Edition', in. Taylor & Francis (Manufacturing engineering and materials processing), p. 525.

Kolli, M. and Kumar, A. (2014) 'Effect of boron carbide powder mixed into dielectric fluid on electrical discharge machining of titanium alloy', in *Procedia Materials Science*. Elsevier, pp. 1957–1965. doi: <https://doi.org/10.1016/j.mspro.2014.07.528>.

Kolli, M. and Kumar, A. (2015) 'Effect of dielectric fluid with surfactant and graphite powder on Electrical Discharge Machining of titanium alloy using Taguchi method', *Engineering Science and Technology, an International Journal*. Elsevier Ltd, 18(4), pp. 524–535. doi: 10.1016/j.jestch.2015.03.009.

Koshy, G., Philip, P. K. and Geddam, A. (1983) 'Hardening of surface layers using electric discharge techniques', in *Proceedings of the 11th AIMTDR Conference*, pp. 315–319.

Koshy, P., Dewes, R. C. and Aspinwall, D. K. (2002) 'High speed end milling of hardened AISI D2 tool steel (~ 58 HRC)', *Journal of Materials Processing Technology*. Elsevier, 127(2), pp. 266–273. doi: [https://doi.org/10.1016/s0924-0136\(02\)00155-3](https://doi.org/10.1016/s0924-0136(02)00155-3).

Kumar, A. *et al.* (2019) 'Comparison in the performance of EDM and NPMEDM using Al₂O₃ nanopowder as an impurity in DI water dielectric', *The International Journal of Advanced Manufacturing Technology*. Springer, 100(5–8), pp. 1327–1339. doi: <https://doi.org/10.1007/s00170-018-3126-z>.

Kumar, A., Bagal, D. K. and Maity, K. P. (2014) 'Numerical Modeling of Wire Electrical Discharge Machining of Super alloy Inconel 718', in *Procedia Engineering*.

Elsevier, pp. 1512–1523. doi: <https://doi.org/10.1016/j.proeng.2014.12.435>.

Kumar, H. (2015) ‘Development of mirror like surface characteristics using nano powder mixed electric discharge machining (NPMEDM)’, *The International Journal of Advanced Manufacturing Technology*. Springer, 76(1–4), pp. 105–113. doi: <https://doi.org/10.1007/s00170-014-5965-6>.

Kumar, N. and Ahsan, R. (2017) ‘Study of PMEDM Efficiency on EN-31 Steel using Tungsten Powder in Dielectric Fluid’, *International Journal of Emerging Technologies in Engineering Research*, 5(5), pp. 17–24.

Kumar, Naveen *et al.* (2016) ‘Study of PMEDM efficiency on HCHCr steel using silicon powder in dielectric fluid’, *Int J Emer Technol Eng Res*, 4, pp. 54–61.

Kumar, S. *et al.* (2009) ‘Surface modification by electrical discharge machining: A review’, *Journal of Materials Processing Technology*. Elsevier, 209(8), pp. 3675–3687. doi: 10.1016/j.jmatprotec.2008.09.032.

Kumar, S., Batish, A., *et al.* (2015a) ‘A mathematical model to predict material removal rate during electric discharge machining of cryogenically treated titanium alloys’, *Proceedings of the Institution of Mechanical Engineers, Part B: Journal of Engineering Manufacture*. SAGE Publications Sage UK: London, England, 229(2), pp. 214–228. doi: 10.1177/0954405414527955.

Kumar, S., Singh, R., *et al.* (2015b) ‘Study the surface characteristics of cryogenically treated tool-electrodes in powder mixed electric discharge machining process’, in *Materials Science Forum*, pp. 19–33. doi: 10.4028/www.scientific.net/MSF.808.19.

Kumar, S. and Batra, U. (2012) ‘Surface modification of die steel materials by EDM method using tungsten powder-mixed dielectric’, *Journal of Manufacturing Processes*. The Society of Manufacturing Engineers, 14(1), pp. 35–40. doi: <https://doi.org/10.1016/j.jmapro.2011.09.002>.

Kumar, Satish, Dhingra, A. K. and Kumar, Sanjeev (2017) 'Parametric optimization of powder mixed electrical discharge machining for nickel- based superalloy inconel-800 using response surface methodology', *Mechanics of Advanced Materials and Modern Processes*. Mechanics of Advanced Materials and Modern Processes, 3(1), pp. 2–17. doi: 10.1186/s40759-017-0022-4.

Kuriachen, B. (2019) 'Powder-Mixed Microelectric Discharge Machining', in *Micro-electrical Discharge Machining Processes*. Springer, pp. 137–159. doi: 10.1007/978-981-13-3074-2_7.

Lajis, M. A. and Hosni, N. A. J.(2018) 'The influences of various mixed dielectric fluids on the performance electrical discharge machining of AISI D2 hardened steel', *Materialwissenschaft und Werkstofftechnik*. Wiley Online Library, 49(3), pp. 413–419. doi: 10.1002/mawe.201700253

Le, V. T. *et al.* (2019) 'Surface Modification Process by Electrical Discharge Machining with Tungsten Carbide Powder Mixing in Kerosene Fluid', in *Applied Mechanics and Materials*, pp. 115–122. doi: 10.4028/www.scientific.net/AMM.889.115.

Leão, F. N. and Pashby, I. R. (2004) 'A review on the use of environmentally-friendly dielectric fluids in electrical discharge machining', *Journal of Materials Processing Technology*. Elsevier, 149(1–3), pp. 341–346. doi: 10.1016/j.jmatprotec.2003.10.043.

Li, X. *et al.* (2011) 'Application of the entropy weight and TOPSIS method in safety evaluation of coal mines', in *Procedia Engineering: First International Symposium on Mine Safety Science and Engineering*. Elsevier, pp. 2085–2091. doi: 10.1016/j.proeng.2011.11.2410.

Long, B. T. *et al.* (2016) 'Optimization of PMEDM process parameter for maximizing material removal rate by Taguchi's method', *The International Journal of Advanced Manufacturing Technology*. Springer, 87(5–8), pp. 1929–1939. doi: 10.1007/s00170-016-8586-4.

M M Sari and M Y Noordin (2012) 'Evaluating the electrical discharge machining (EDM) parameters with using carbon nanotubes', *IOP Conf. Series: Materials Science and Engineering*, 40(conference 1). doi: 10.1088/1757-899X/40/1/012019.

M.Galindo Fernandez, C. Diverb ,W. Leahyc (2016) 'The prediction of surface finish and cutting speed for wire electro-discharge machining of Polycrystalline Diamond', *18th CIRP Conference on Electro Physical and Chemical Machining (ISEM XVIII)*. doi: 10.1016/j.procir.2016.02.289.

Mai, C., Hocheng, H. and Huang, S. (2012) 'Advantages of carbon nanotubes in electrical discharge machining', *The International Journal of Advanced Manufacturing Technology*. Springer, 59(1–4), pp. 111–117. doi: 10.1007/s00170-011-3476-2.

MakeItFrom, M. P. D. (2009) Hardened D2 Tool Steel, MakeItFrom. Retrieved January 10th 2019. From <https://www.makeitfrom.com/material-properties/Hardened-D2-Tool-Steel>.

Mandal, P. and Mondal, S. C. (2019) 'Development and application of Cu-SWCNT nanocomposite--coated 6061Al electrode for EDM', *The International Journal of Advanced Manufacturing Technology*. Springer, pp. 1–10.

Marashi, H., Sarhan, A. A. D. and Hamdi, M. (2015) 'Employing Ti nano-powder dielectric to enhance surface characteristics in electrical discharge machining of AISI D2 steel', *Applied Surface Science*. Elsevier, 357, pp. 892–907. doi: 10.1016/j.apsusc.2015.09.105.

Ming, Q. Y. and He, L. Y. (1995) 'Powder-suspension dielectric fluid for EDM', *Journal of materials processing technology*. Elsevier, 52(1), pp. 44–54. doi: 10.1016/0924-0136(94)01442-4.

Ming, W. *et al.* (2014) 'A hybrid process model for EDM based on finite-element method and Gaussian process regression', *The International Journal of Advanced Manufacturing Technology*. Springer, 74(9–12), pp. 1197–1211. doi:

<https://doi.org/10.1007/s00170-014-5989-y>.

Mir, M. J. *et al.* (2012) 'Modeling and analysis of machining parameters for surface roughness in powder mixed EDM using RSM approach', *International Journal of Engineering, Science and Technology*, 4(3), pp. 45–52.

Mitutoyo America Corporation (2016) *Quick guide to surface roughness measurement. Bulletin No. 2229*. doi: 10.3886/ICPSR31521.v1.

Miyazaki, T. *et al.* (1995) 'Surface modification of steel by a small-diameter plasma arc', *CIRP annals*. Elsevier, 44(1), pp. 161–164. doi: 10.1016/S0007-8506(07)62297-5.

Mohammad Y A (2012) 'Powder Mixed Micro Electro Discharge Milling of Titanium Alloy: Analysis of Surface Roughness', *Advanced Materials Research*, 342, pp. 142–146. doi: 10.4028/www.scientific.net/AMR.341-342.142.

Mohanty, C. P., Sahu, J. and Mahapatra, S. S. (2013) 'Thermal-structural analysis of electrical discharge machining process', *Procedia Engineering*. Elsevier, 51, pp. 508–513.

Mohanty, S. *et al.* (2019) 'Surface modification of Ti-alloy by micro-electrical discharge process using tungsten disulphide powder suspension', *Journal of Manufacturing Processes*. Elsevier, 37, pp. 28–41. doi: 10.1016/j.jmapro.2018.11.007.

Molinetti, A. *et al.* (2016) 'Surface modification of AISI H13 tool steel with silicon or manganese powders mixed to the dielectric in electrical discharge machining process', *The International Journal of Advanced Manufacturing Technology*. Springer, 83(5–8), pp. 1057–1068. doi: 10.1007/s00170-015-7613-1.

Montgomery, D. C. (2017) *Design and Analysis of Experiments*. John Wiley & Sons, Incorporated.

Myers, R. H., Montgomery, D. C. and Anderson-Cook, C. M. (2016) *Response Surface Methodology: Process and Product Optimization Using Designed Experiments*. Wiley (Wiley Series in Probability and Statistics).

Naidu, M. S. and Kamaraju, V. (2013) *High Voltage Engineering*. McGraw Hill Education (India). Available at: <https://books.google.com.my/books?id=NiLZAgAAQBAJ>.

Nguyen, H.-P., Pham, V.-D. and Ngo, N.-V. (2018) ‘Application of TOPSIS to Taguchi method for multi-characteristic optimization of electrical discharge machining with titanium powder mixed into dielectric fluid’, *The International Journal of Advanced Manufacturing Technology*. Springer, 98(5–8), pp. 1–20. doi: <https://doi.org/10.1007/s00170-018-2321-2>.

Ojha, K., Garg, R. K. and Singh, K. K. (2011) ‘Effect of chromium powder suspended dielectric on surface roughness in PMEDM process’, *Tribology-Materials, Surfaces & Interfaces*. Taylor & Francis, 5(4), pp. 165–171. doi: 10.1179/1751584X11Y.00000000021.

Okada, A. (2000) ‘Formation of Hard Layer by EDM with Carbon Powder Mixed Fluid’, in *Proc. of the 5th International Conference on Progress of Machining Technology*, pp. 464–469.

Ostwald, P. F. and Munoz, J. (2008) ‘Manufacturing Processes And Systems, 9Th Ed’, in. Wiley India Pvt. Limited, pp. 480–482.

Özel, T. *et al.* (2007) ‘Modelling of surface finish and tool flank wear in turning of AISI D2 steel with ceramic wiper inserts’, *Journal of materials processing technology*. Elsevier, 189(1), pp. 192–198.

Pandey, A. K. and Dubey, A. K. (2012) ‘Simultaneous optimization of multiple quality characteristics in laser cutting of titanium alloy sheet’, *Optics & Laser Technology*.

Elsevier, 44(6), pp. 1858–1865.

Patel, S., Thesiya, D. and Rajurkar, A. (2018) ‘Aluminium powder mixed rotary electric discharge machining (PMEDM) on Inconel 718’, *Australian Journal of Mechanical Engineering*. Taylor & Francis, 16(1), pp. 21–30. doi: 10.1080/14484846.2017.1294230.

Pecas, P. and Henriques, E. (2003) ‘Influence of silicon powder-mixed dielectric on conventional electrical discharge machining’, *International Journal of Machine Tools and Manufacture*. Elsevier, 43(14), pp. 1465–1471. doi: 10.1016/S0890-6955(03)00169-X.

Peças, P. and Henriques, E. (2008) ‘Effect of the powder concentration and dielectric flow in the surface morphology in electrical discharge machining with powder-mixed dielectric (PMD-EDM)’, *The International Journal of Advanced Manufacturing Technology*. Springer, 37(11–12), pp. 1120–1132. doi: 10.1007/s00170-007-1061-5.

Prabhu and Vinayagam (2013) ‘AFM Nano Analysis of Inconel 825 with Single Wall Carbon Nano Tube in Die Sinking EDM Process Using Taguchi Analysis’, *Arabian Journal for Science and Engineering*, 38(6), pp. 1599–1613. doi: 10.1007/s13369-012-0348-5.

Prabhu, S. and Vinayagam, B. K. (2012) ‘Modeling the machining parameters of AISI D2 tool steel material with multi wall carbon nano tube in electrical discharge machining process using response surface methodology’, *International Journal of the Physical Sciences*, 7(2), pp. 297–305. doi: 10.5897/ijps10.564.

Prabhu, S. and Vinayagam, B. K. (2016) ‘Multiresponse optimization of EDM process with nanofluids using TOPSIS method and genetic algorithm’, *Archive of Mechanical Engineering*. De Gruyter Open, 63(1), pp. 45–71. doi: 10.1515/meceng-2016-0003.

Pradhan, M. K. and Biswas, C. K. (2009a) ‘Modeling and Analysis of process parameters on Surface Roughness in EDM of AISI D2 tool Steel by RSM Approach’.

Nova Science Publishers, USA.

Pradhan, M. K. and Biswas, C. K. (2009b) 'Neuro-fuzzy model and regression model a comparison study of MRR in electrical discharge machining of D2 tool steel'. Nova Science Publishers, USA.

Prakash, C. *et al.* (2016) 'Multi-objective optimization of powder mixed electric discharge machining parameters for fabrication of biocompatible layer on β -Ti alloy using NSGA-II coupled with Taguchi based response surface methodology', *Journal of Mechanical Science and Technology*. Springer, 30(9), pp. 4195–4204. doi: 10.1007/s12206-016-0831-0.

Prakash, C. *et al.* (2017) 'Experimental investigations in powder mixed electric discharge machining of Ti-35Nb-7Ta-5Zr β -titanium alloy', *Materials and Manufacturing Processes*. Taylor & Francis, 32(3), pp. 274–285. doi: 10.1080/10426914.2016.1198018.

Prihandana, G. S. and Sriani, T. (2014) 'Application of powder suspended in dielectric fluid for fine finish micro-EDM of Inconel 718', *The International Journal of Advanced Manufacturing Technology*, 75(1–4), pp. 599–613. doi: 10.1007/s00170-014-6145-4.

Prihandana, G. S., Sriani, T. and Mahardika, M. (2012) 'Improvement of machining time in micro-EDM with workpiece vibration and graphite powder mixed in dielectric fluid'. NISCAIR-CSIR, India.

Rajendra, M. and Rao, G. K. M. (2014) 'Experimental Evaluation of Performance of Electrical Discharge Machining of D3 Die Steel with Al₂O₃ Abrasive Mixed Dielectric Material by Using Design of Experiments', *International Journal of Research in Engineering and Technology*, 3(1), pp. 599–606.

Rao, S. S. (1989) 'The Finite Element Method in Engineering', in. Pergamon Press, pp. 474, 541–542. Available at: <https://books.google.com.my/books?id=1IIoAQAAMAAJ>.

Rathi, M. G. and Mane, D. V (2014) 'Study on Effect of Powder Mixed dielectric in EDM of Inconel 718', *International Journal of Scientific and Research Publications*, 4(11), pp. 1–7.

Reddy, V. V. and Madar, A. K. P. (2015) 'Influence of surfactant and graphite powder concentration on electrical discharge machining of PH17-4 stainless steel', *Journal of the Brazilian Society of Mechanical Sciences and Engineering*, 37(2), pp. 641–655. doi: 10.1007/s40430-014-0193-4.

Reddy, V. V., Madarvalli, P. and Reddy, C. S. (2015) 'Micro Hardness Measurements on Machined Surface of PH17-4 Stainless Steel during EDM with Surfactant and Graphite Powder Mixed Dielectric', *Journal of Material Science and Mechanical Engineering*, 2(3), pp. 243–247.

Roberts, G. A., Kennedy, R. and Krauss, G. (1998) 'Tool Steels, Fifth Edition', in. ASM International (EngineeringPro collection), pp. 16–17. Available at: https://books.google.com.my/books?id=ScphevR_eP8C.

Roy, C., Syed, K. H. and Kuppan, P. (2016) 'Machinability of Al/ 10%SiC/ 2.5%TiB₂ Metal Matrix Composite with Powder-mixed Electrical Discharge Machning', in *Procedia Technology: Global Colloquium in Recent Advancement and Effectual Researches in Engineering, Science and Technology (RAEREST 2016)*. The Author(s), pp. 1056–1063. doi: 10.1016/j.protcy.2016.08.206.

S. Tripathy and D.K Tripathy (2016) 'Multi-response optimization of machining process parameters for powder mixed electro-discharge machining of H-11 die steel using grey relational analysis and topsis', *Machining Science and Technology*. Taylor & Francis, 21(3), pp. 1–23. doi: 10.1080/10910344.2017.1283957.

Saaty, T. L. (1990) *Decision making for leaders: the analytic hierarchy process for decisions in a complex world*. RWS publications.

Sahu, J., Mohanty, C. P. and Mahapatra, S. S. (2013) 'A DEA approach for optimization of multiple responses in electrical discharge machining of AISI D2 steel', *Procedia Engineering*. Elsevier, 51, pp. 585–591.

Salonitis, K. *et al.* (2009) 'Thermal modeling of the material removal rate and surface roughness for die-sinking EDM', *The International Journal of Advanced Manufacturing Technology*. Springer, 40(3), pp. 316–323. doi: 10.1007/s00170-007-1327-y.

Sanghani, C. R., Acharya, G. D. and Kothari, K. D. (2016) 'Trends in Machine Design Finite Element Analysis of Tool Wear Rate in Electrical Discharge Machining and Comparison with Experimental Results', *Trends in Machine Design*, 3(3), pp. 18–22.

Sari, M. M., Noordin, M. Y. and Brusa, E. (2013) 'Role of multi-wall carbon nanotubes on the main parameters of the electrical discharge machining (EDM) process', *The International Journal of Advanced Manufacturing Technology*, 68(5–8), pp. 1095–1102. doi: 10.1007/s00170-013-4901-5.

Savic, D. (2002) 'Single-objective vs. multiobjective optimisation for integrated decision support'.

Scott, D. (2013) 'Wear: Treatise on Materials Science and Technology', in. Elsevier Science, pp. 9–11. Available at: <https://books.google.com.my/books?id=3kcvBQAAQBAJ>.

Sergiu, N. A., Ion, M. N. and Daniel, G. L. (2013) 'ESTIMATIONS ON MAIN MANUFACTURING ELEMENTS OF COST SPECIFIC TO EDM OPERATIONS.', *Nonconventional Technologies Review/Revista de Tehnologii Neconventionale*, 17(4).

Severin, K. P. (2008) *Energy Dispersive Spectrometry of Common Rock Forming Minerals*. Springer Netherlands. Available at: <https://books.google.com.my/books?id=zJHwBwAAQBAJ>.

Sezer, H. K. *et al.* (2006) 'Effect of beam angle on HAZ, recast and oxide layer characteristics in laser drilling of TBC nickel superalloys', *International Journal of Machine Tools and Manufacture*. Elsevier, 46(15), pp. 1972–1982. doi: 10.1016/j.ijmachtools.2006.01.010.

Shabgard, M. *et al.* (2011) 'Experimental investigation and 3D finite element prediction of the white layer thickness, heat affected zone, and surface roughness in EDM process', *Journal of mechanical science and technology*. Springer, 25(12), pp. 3173–3183. doi: <https://doi.org/10.1007/s12206-011-0905-y>.

Shabgard, M. *et al.* (2013) 'Mathematical and numerical modeling of the effect of input-parameters on the flushing efficiency of plasma channel in EDM process', *International Journal of Machine Tools and Manufacture*. Elsevier, 65, pp. 79–87. doi: 10.1016/j.ijmachtools.2012.10.004.

Shabgard, M. and Khosrozadeh, B. (2017) 'Investigation of carbon nanotube added dielectric on the surface characteristics and machining performance of Ti-6Al-4V alloy in EDM process', *Journal of Manufacturing Processes*. The Society of Manufacturing Engineers, 25, pp. 212–219. doi: 10.1016/j.jmapro.2016.11.016.

Shabgard, M. R. and Kabirinia, F. (2014) 'Effect of dielectric liquid on characteristics of WC-Co powder synthesized using EDM process', *Materials and Manufacturing Processes*. Taylor & Francis, 29(10), pp. 1269–1276. doi: 10.1080/10426914.2013.852207.

Sharbari, B. (2011) *Avoiding Sample Preparation Pitfalls in Materials Analysis, Quality Digest*. Available at: <https://www.qualitydigest.com/inside/metrology-article/avoiding-sample-preparation-pitfalls-materials-analysis-012611.html> (Accessed: 13 September 2019).

Sharma, S. *et al.* (2010) 'Effect of aluminium powder addition in dielectric during electric discharge machining of hastelloy on machining performance using reverse

polarity', *International Journal of Advanced Engineering Technology*, 1(3), pp. 13–24.

Sheu, D. (2017) 'Experimental Investigation Nano Particles Influence in NPMEDM to Machine Inconel 800 with Electrolyte Copper Electrode', *IOP Conference Series: Materials Science and Engineering*, 197(1). doi: 10.1088/1757-899X/197/1/012068.

Singh, A. K., Kumar, S. and Singh, V. P. (2015) 'Effect of the addition of conductive powder in dielectric on the surface properties of superalloy Super Co 605 by EDM process', *The International Journal of Advanced Manufacturing Technology*. Springer, 77(1–4), pp. 99–106. doi: 10.1007/s00170-014-6433-z.

Singh, B., Kumar, J. and Kumar, S. (2015) 'Influences of process parameters on MRR improvement in simple and powder-mixed EDM of AA6061/10% SiC composite', *Materials and Manufacturing Processes*. Taylor & Francis, 30(3), pp. 303–312. doi: 10.1080/10426914.2014.930888.

Singh, C. D. (2018) 'Electrical Discharge Machining. Optimization of Chromium Powder Mixed EDM Parameters During Machining of H13 Tool Steel', in. Anchor Academic Publishing, pp. 10–13. Available at: <https://books.google.com.my/books?id=TZZHDwAAQBAJ>.

Singh, G. *et al.* (2012) 'Effect of machining parameters on surface roughness of H13 steel in EDM process using powder mixed fluid', *International journal of advanced engineering research and studies*, 2(1), pp. 148–150.

Singh, H. (2012) 'Experimental study of distribution of energy during EDM process for utilization in thermal models', *International Journal of Heat and Mass Transfer*. Elsevier, 55(19–20), pp. 5053–5064. doi: 10.1016/j.ijheatmasstransfer.2012.05.004.

Singh, J. and Sharma, R. K. (2016) 'Implementation of Taguchi method with hybrid decision making tools for prediction of surface characteristics for Powder-mixed EDM of WC', *Perspectives in Science*. Elsevier GmbH, 8, pp. 455–458. doi:

10.1016/j.pisc.2016.04.103.

Singh, M. A., Das, K. and Sarma, D. K. (2018) 'Thermal simulation of machining of alumina with wire electrical discharge machining process using assisting electrode', *Journal of Mechanical Science and Technology*. Springer, 32(1), pp. 333–343. doi: 10.1007/s12206-017-1233-7.

Singh, M. and Jessen, T. (2009) '25th Annual Conference on Composites, Advanced Ceramics, Materials, and Structures - B', in. Wiley (Ceramic Engineering and Science Proceedings), pp. 27–34. Available at: https://books.google.com.my/books?id=vY3TIG0_4loC.

Singh, P. *et al.* (2010a) 'Influence of electrical parameters in powder mixed electric discharge machining (PMEDM) of hastelloy', *Journal of Engineering Research and Studies*, 1(2), pp. 93–105.

Singh, P. *et al.* (2010b) 'Some Experimental investigation on aluminum powder mixed EDM on machining performance of hastelloy steel', *International Journal of Advanced Engineering Technology*, 1(2), pp. 28–45.

Singh, S. *et al.* (2012) 'Optimization of Abrasive Powder Mixed EDM of Aluminum Matrix Composites with Multiple Responses Using Gray Relational Analysis', *Journal of Materials Engineering and Performance*, 21(April), pp. 481–491. doi: 10.1007/s11665-011-9861-z.

Singh, S. and Yeh, M.-F. (2012) 'Optimization of abrasive powder mixed EDM of aluminum matrix composites with multiple responses using gray relational analysis', *Journal of materials engineering and performance*. Springer, 21(4), pp. 481–491. doi: 10.1007/s11665-011-9861-z.

Snoeys, R. (1971) 'Investigations of EDM operations by means of thermomathematical models', *Annals of the CIRP*, 20, pp. 35–36.

Somashekhar, K. P., Ramachandran, N. and Mathew, J. (2010) 'Optimization of material removal rate in micro-EDM using artificial neural network and genetic algorithms', *Materials and Manufacturing Processes*. Taylor & Francis, 25(6), pp. 467–475. doi: 10.1080/10426910903365760.

Sugunakar, A., Kumar, A. and Markandeya, R. (2017) 'Effect of Powder Mixed Dielectric fluid on Surface Integrity by Electrical Discharge Machining of RENE 80', *Journal of Mechanical and Civil Engineering*, 14(3), pp. 43–50.

Syed, K. H. and Palaniyandi, K. (2012) 'Performance of electrical discharge machining using aluminium powder suspended distilled water', *Turkish Journal of Engineering and Environmental Sciences*. The Scientific and Technological Research Council of Turkey, 36(3), pp. 195–207. doi: 10.3906/muh-1202-2.

Talla, G., Sahoo, D. K., Gangopadhyay, S, *et al.* (2015) 'Modeling and multi-objective optimization of powder mixed electric discharge machining process of aluminum/alumina metal matrix composite', *Engineering Science and Technology, an International Journal*. Elsevier, 18(3), pp. 369–373. doi: 10.1016/j.jestch.2015.01.007.

Talla, G., Gangopadhyay, S. and Biswas, C. K. (2016) 'Effect of Powder-Suspended Dielectric on the EDM Characteristics of Inconel 625', *Journal of Materials Engineering and Performance*. Springer US, 25(2), pp. 704–717. doi: 10.1007/s11665-015-1835-0.

Tan, P. C. and Yeo, S. H. (2013) 'Simulation of surface integrity for nanopowder-mixed dielectric in micro electrical discharge machining', *Metallurgical and Materials Transactions B: Process Metallurgy and Materials Processing Science*, 44(3), pp. 711–721. doi: 10.1007/s11663-013-9819-7.

Tawfiq, M. A. and Hameed, A. S. (2015) 'Effect of powder concentration in PMEDM on surface roughness for different die steel types', *International Journal of Current Engineering and Technology*, 5, pp. 3323–3329.

Taylor, P. *et al.* (2012) 'Machining Efficiency Evaluation of Cryogenically Treated Copper Electrode in Additive Mixed EDM Machining Efficiency Evaluation of Cryogenically Treated Copper Electrode in Additive Mixed EDM', *Materials and Manufacturing Processes*, 27(September 2012), pp. 1051–1058. doi: 10.1080/10426914.2011.654151.

Thakurathi, M. *et al.* (2018) 'The Stokes-Einstein equation and the diffusion of ferrocene in imidazolium-based ionic liquids studied by cyclic voltammetry: Effects of cation ion symmetry and alkyl chain length', *Electrochimica Acta*. Elsevier, 259, pp. 245–252.

Toshimitsu, R. *et al.* (2016) 'Improvement in Surface Characteristics by EDM with Chromium Powder Mixed Fluid', *Procedia CIRP*. Elsevier B.V., 42(Isem Xviii), pp. 231–235. doi: 10.1016/j.procir.2016.02.277.

Trachioti, M. G. *et al.* (2019) 'Extended coverage of screen-printed graphite electrodes by spark discharge produced gold nanoparticles with a 3D positioning device. Assessment of sparking voltage-time characteristics to develop sensors with advanced electrocatalytic properties', *Electrochimica Acta*. Elsevier. doi: 10.1016/j.electacta.2019.03.004.

Tripathy, S. and Tripathy, D. K. (2017a) 'Multi-response optimization of machining process parameters for powder mixed electro-discharge machining of H-11 die steel using grey relational analysis and topsis', *Machining Science and Technology*. Taylor & Francis, 21(3), pp. 362–384. doi: 10.1080/10910344.2017.1283957.

Tripathy, S. and Tripathy, D. K. (2017b) 'Optimization of Process Parameters and Investigation on Surface Characteristics During EDM and Powder Mixed EDM', in *Innovative design and development practices in Aerospace and Automotive Engineering*. Springer, pp. 385–391. doi: 10.1007/978-981-10-1771-1_41.

Tripathy, S. and Tripathy, D. K. (2018) 'Optimization of Process Parameters in Powder-

Mixed EDM', in *Precision Product-Process Design and Optimization*. Springer, pp. 239–283. doi: 10.1007/978-981-10-8767-7_10.

Tzeng, Y.-F. and Lee, C.-Y. (2001) 'Effects of powder characteristics on electrodischarge machining efficiency', *The International Journal of advanced manufacturing technology*. Springer, 17(8), pp. 586–592. doi: <https://doi.org/10.1007/s001700170142>.

Unses, E. and Cogun, C. (2015) 'Improvement of electric discharge machining (EDM) performance of Ti-6Al-4V alloy with added graphite powder to dielectric/Izboljsanje elektroerozijske (EDM) obdelave zlitine Ti-6Al-4V z dodatkom grafitnega prahu v dielektriku', *Strojniski Vestnik-Journal of Mechanical Engineering*. University of Ljubljana, Faculty of Mechanical Engineering, 61(6), pp. 409–420. doi: <https://doi.org/10.5545/sv-jme.2015.2460>.

Uthayakumar, M. *et al.* (2019) 'Evaluation of Electrical Discharge Machining Performance on Al (6351)--SiC--B4C Composite', in *Non-Conventional Machining in Modern Manufacturing Systems*. IGI Global, pp. 109–124. doi: 10.4018/978-1-5225-6161-3.ch005.

Vajpayee, S. S. *et al.* (2015) 'Optimization of Response Parameter On Textile Machine Using GRA-TOPSIS Approach', *International Journal of Advanced Research*, 3, pp. 20–28.

Wainerdi, R. (2012) *Modern Methods of Geochemical Analysis*. Springer US (Monographs in Geoscience). Available at: <https://books.google.com.my/books?id=9DDoBwAAQBAJ>.

Walker, H. F. (2008) 'The Certified Quality Inspector Handbook', in. ASQ Quality Press, pp. 98–99. Available at: <https://books.google.com.my/books?id=Yc0DI-YjlWsC>.

Wang, C.-C. *et al.* (2009) 'Recast layer removal after electrical discharge machining via

Taguchi analysis: a feasibility study', *Journal of Materials Processing Technology*. Elsevier, 209(8), pp. 4134–4140. doi: 10.1016/j.jmatprotec.2008.10.012Get.

Wang, C. and Qiang, Z. (2019) 'Comparison of Micro-EDM Characteristics of Inconel 706 between EDM Oil and an Al Powder-Mixed Dielectric', *Advances in Materials Science and Engineering*. Hindawi, 2019. doi: 10.1155/2019/5625360.

Wang, X. *et al.* (2016) 'Characteristics of plasma channel in powder-mixed EDM based on monopulse discharge', *The International Journal of Advanced Manufacturing Technology*. Springer, 82(5–8), pp. 1063–1069. doi: 10.1007/s00170-015-7236-6.

Wansheng, Z. *et al.* (1995) 'A measuring and evaluating system of the utilization ratio of electrical energy in EDM', in *Proceedings of the 11th International Symposium on Electromachining (ISEM XI), Lausanne, Switzerland*, pp. 253–259.

Wong, Y. S. *et al.* (1998) 'Near-mirror-finish phenomenon in EDM using powder-mixed dielectric', *Journal of Materials Processing Technology*. Elsevier, 79(1–3), pp. 30–40. doi: [https://doi.org/10.1016/s0924-0136\(97\)00450-0](https://doi.org/10.1016/s0924-0136(97)00450-0).

Wu, D. and Olson, D. L. (2006) 'A TOPSIS data mining demonstration and application to credit scoring', *International Journal of Data Warehousing and Mining (IJDWM)*. IGI Global, 2(3), pp. 16–26. doi: 10.4018/jdwm.2006070102.

XIE, B. *et al.* (2011) 'Numerical simulation of titanium alloy machining in electric discharge machining process', *Transactions of Nonferrous Metals Society of China*. Elsevier, 21, pp. s434--s439. doi: 10.1016/S1003-6326(11)61620-8.

Yaşar, H. and Ekmekci, B. (2014) 'Ti-6Al-4V Surfaces in SiC Powder Mixed Electrical Discharge Machining', *Advanced Materials Research*, 856, pp. 226–230. doi: 10.4028/www.scientific.net/AMR.856.226.

Yeo, S. H., Kurnia, W. and Tan, P. C. (2008) 'Critical assessment and numerical

comparison of electro-thermal models in EDM', *Journal of Materials Processing Technology*, 203(1–3), pp. 241–251. doi: 10.1016/j.jmatprotec.2007.10.026.

Yih-Fong, T. and Fu-Chen, C. (2005) 'Investigation into some surface characteristics of electrical discharge machined SKD-11 using powder-suspension dielectric oil', *Journal of Materials Processing Technology*. Elsevier, 170(1–2), pp. 385–391. doi: <https://doi.org/10.1016/j.jmatprotec.2005.06.006>.

Youssef, H. A. and El-Hofy, H. (2008) 'Machining Technology: Machine Tools and Operations', in. CRC Press, p. 575. Available at: <https://books.google.com.my/books?id=IleBqfaGK1oC>.

Zhang, Y. *et al.* (2013) 'A new method of investigation the characteristic of the heat flux of EDM plasma', *Procedia CIRP*. Elsevier, 6, pp. 450–455.

Zhang, G. *et al.* (2018) 'Study on the effect of three dimensional wire vibration on WEDM based on a novel thermophysical model', *The International Journal of Advanced Manufacturing Technology*, 96(443), pp. 1997–2020. doi: 10.1007/s00170-018-2796-x.

Zhao, W. S., Meng, Q. G. and Wang, Z. L. (2002) 'The application of research on powder mixed EDM in rough machining', *Journal of materials processing technology*. Elsevier, 129(1–3), pp. 30–33. doi: 10.1016/S0924-0136(02)00570-8.

Zingerman, A. S. (1956) 'The effect of thermal conductivity upon the electrical erosion of metals', *Soviet Phys.-Tech. Phys.*